

LaRonde Operations Summary

AEM

LaRonde Operations Summary	2008	2009	2010	2011	2012-2017 Average
Ore (000's tonnes)	2,635	2,580	2,585	2,560	2,435
Grades:					
Gold (g/t)	2.80	2.73	2.45	2.80	5.18
Silver (g/t)	68.38	72.96	71.82	62.88	31.26
Zinc (%)	3.65	3.63	3.71	2.79	1.45
Copper (%)	0.35	0.36	0.28	0.33	0.31
Mill recovery (%):					
Gold	91	91	91	91	94
Silver	85	85	85	86	72
Zinc	88	88	89	86	75
Copper	86	86	84	86	85
Payable metal:					
Gold (oz)	215,891	205,801	184,434	209,608	381,183
Silver (oz 000's)	4,241	4,459	4,388	3,874	1,577
Zinc (t)	72,266	70,470	72,359	52,365	23,130
Copper (t)	7,387	7,363	5,463	6,610	6,042
Minesite costs (C\$/t)	66	67	69	69	67